



663 W. 2<sup>nd</sup> Ave. #15 Mesa, AZ 85210  
480-970-4580 ♦ 480-421-6322 (fax)  
[www.surfacegeltek.com](http://www.surfacegeltek.com)  
[info@surfacegeltek.com](mailto:info@surfacegeltek.com)  
[tamryn@surfacegeltek.com](mailto:tamryn@surfacegeltek.com)

## Effects on Surface Gel Tek's Gelled Acid Products When Exposed to Freezing Temperatures

Test Date: March 29, 2003 through April 7, 2003  
Report Date: April 7, 2003  
Products Tested: **TEK GEL™ Profiling**  
**HD24 Pre Grind**  
**TEK GEL™ Flattooing™**

1. Three 7 oz. containers of above products were exposed to <math>5^{\circ}</math> F for 10 days.
2. Immediately upon removal from freezing environment, products were examined:

No crystallization was observed  
Products remained gelled  
Products mixed well

3. Products were applied to concrete surface and immediate reaction with the concrete surface was observed. Products performed in the same manner as before exposure to freezing temperatures.

Results: No negative effect was observed when exposed to freezing temperatures.